

<b>Document Name</b>	Document No.	Ver	Date	Page
LP402040 Specification	ZJQM-RD-SPC-A0747	0.0	2015-2-11	1/7

# EEMB CO., LTD

# Polymer Li-ion Battery Specification

**Model:** LP402040

Capacity: 270mAh

Prepared	Checked	Approved

#### Customer:

Customer Approval	(Customer confirmation):	
	1	
Signature	Checked	Approved

Address: Room ABCD,25/F, Block A, Fortune Plaza, NO.7060 Shennan Road Shenzhen, China

Postal code: 518040

Phone: 0086-755-83022275 FAX: 0086-755-83021966

http://www.eemb.com



<b>Document Name</b>	Document No.	Ver	Date	Page
LP402040 Specification	ZJQM-RD-SPC-A0747	0.0	2015-2-11	2/7

# Catalog

Chapter	Content	Page
0	Catalog.	2
1	Scope	3
2	Product Basic Characteristics.	3
2.1	Model	3
2.2	Capacity	3
2.3	Nominal Voltage	3
2.4	Weight	3
2.5	Internal Impedance	3
2.6	Dimension	3
2.7	Charge	3
2.8	Discharge	3
2.9	Operation Temperature	3
2.10	Storage Temperature	3
2.11	Storage Relative Humidity	3
3	Shape and Dimensions.	3
4	Appearance	4
5	Specification	4
5.1	Electrical Characteristics.	4
5.1.1	1C <sub>5</sub> A rate discharge capacity	4
5.1.2	High temp. discharge capacity	4
5.1.3	Low temp. discharge capacity	4
5.1.4	Cycle Life	4
5.1.5	Capacity Retention.	4
5.2	Acclimatization Characteristics.	4
5.2.1	High Temp. and High Humidity	4
5.2.2	Vibration	4
5.2.3	Drop.	4
5.2.4	Low-pressure.	4
5.3	Safety Characteristics.	5
5.3.1	Overcharge.	5
5.3.2	Short-Circuit.	5
5.3.3	Heating.	5
5.3.4	Temperature cycle.	5
6	Battery shipment voltage.	5
7	Shelf life	5
8	Matters needing attention.	5~7



<b>Document Name</b>	Document No.	Ver	Date	Page
LP402040 Specification	ZJQM-RD-SPC-A0747	0.0	2015-2-11	3/7

#### 1. Scope


This product specification defines the requirements of the rechargeable polymer lithium-ion battery supplied to the customer by EEMB Co., Ltd.

#### 2. Product Basic Characteristics

No.		Item	Characteristics		Remark
2.1		Model	LP402040		
2.2	Capacity	Nominal Capacity	270	mAh	$0.2C_5A$
2.2	Сараспу	Minimum	250	mAh	$0.2C_5A$
2.3	Nom	inal Voltage	3.7	V	
2.4		Weight	Approx. 5.4	g	
2.5	Intern	al Impedance	≤ 180	mΩ	AC 1KHz
		Length	≤ 41	mm	
2.6	Dimension	Width	≤ 20.5	mm	
		Thickness	≤ 4.3	mm	
	Charge	Maximum Current	270	mA	1C <sub>5</sub> A (CC&CV)
2.7		Limited Voltage	$4.200\pm0.020$	V	
		End-of Current	5.4	mA	
2.8	Discharge	Maximum Current	540	mA	2.0C <sub>5</sub> A
2.0	Discharge	End Voltage	$2.750\pm0.005$	V	
2.9	Operation	Charge	0 ~ 45	$^{\circ}\!\mathbb{C}$	
2.9	Temperature	Discharge	<b>-</b> 20 ∼ +60	$^{\circ}$	
	Stomage	1 month	<b>-</b> 20 ∼ +60	$^{\circ}\!\mathbb{C}$	
2.10	Storage Temperature	3 month	<b>-</b> 20 ∼ +45	$^{\circ}$	
	Temperature	12 month	<b>-</b> 20 ∼ +25	$^{\circ}$	
2.11	Storage R	elative Humidity	65±20	%	

### 3. Shape and Dimensions (Unit: mm)

Item	Specification
T	Max4.3
W	Max20.5
L	Max41
L1	Max42
L2	10±1
M	9±1
N	2±0.5





<b>Document Name</b>	Document No.	Ver	Date	Page
LP402040 Specification	ZJQM-RD-SPC-A0747	0.0	2015-2-11	4/7

#### 4. Appearance

It shall be free from any defects such as remarkable scratches, breaks, cracks, discoloration, leakage, or middle deformation

#### 5. Specification

#### **5.1 Electrical Characteristics**

No.	Item	Criteria	Test Instructions
5.1.1	1C <sub>5</sub> A rate discharge capacity	Discharge Capacity≥ Minimum Capacity	Full charge at $20\pm5$ °C, rest for 60 min, then discharge at the same temperature with $1.0C_5A$ to $2.75V$ .
5.1.2	High temp. discharge capacity	Discharge Time≥54min	Full charge at $20\pm5$ °C, store at $55\pm2$ °C for 2h, then discharge at the same temperature with $1.0C_5A$ to $2.75V$ .
5.1.3	Low temp. discharge capacity	Discharge Time≥4.25h	Full charge at $20\pm5$ °C, store at $-10$ °C $\pm2$ °C for $16h\sim24h$ , then discharge at the same temperature with $0.2C_5A$ to $2.75V$
5.1.4	Cycle Life	•	After full charge, rest for 10 min, then discharge at constant current to 2.75V, rest for 10 minutes. Repeat above steps until the two consecutive cycles of discharge time is less than the regulated time. (500 cycles > 96min, 800 cycles > 240min)
5.1.5	Capacity Retention	Discharge Time≥4.5 h	After full charge, store at $20\pm5^{\circ}\mathrm{C}$ for 28 days. Then discharge with $0.2C_5A$ to $2.75V$

#### **5.2** Acclimatization Characteristics

No.	Item	Criteria	Test Instructions
5.2.1	High Temp. and High Humidity	or explosion;	After full charge, store at $40^{\circ}\text{C} \pm 2^{\circ}\text{C} (90\% \sim 95\%\text{RH})$ for 48h. After test, place at $20^{\circ}\text{C} \pm 5^{\circ}\text{C}$ for 2h and then discharge with $1\text{C}_5\text{A}$ to end-voltage
5.2.2	Vibration	e or explosion; Battery Voltage>3 6V	Batteries are vibrated 30 min in three mutually perpendicular directions with amplitude of 0.38mm (10~30Hz) or 0.19mm (30~55Hz) and the scanning rate of loct per min
5.2.3	Drop	No leakage, no fire or explo sion; Discharge Time≥51 min	Batteries are dropped onto a hard board with the thickness of 18~20mm from 1meter
5.2.4	Low-pressure	No leakage, no fire or explosion	Put the batteries in a sealed vacuum and reduce internal pressure gradually to lower than 11.6 kpa. Keep for 6h



<b>Document Name</b>	Document No.	Ver	Date	Page
LP402040 Specification	ZJQM-RD-SPC-A0747	0.0	2015-2-11	5/7

#### **5.3 Safety Characteristics**

No.	Item	Criteria	Test Instructions
5.3.1	Overcharge	No fire or evolosion	Charged the cells at $3C_5A$ current $20\pm5^{\circ}C$ with a voltage limit of $4.8V$ and Current close to $0~A$
5.3.2	Short-Circuit	No fire or explosion; The maximum Temperature: 150°C.	Place the battery with thermocouple into a fume hood, and short-circuit by connecting the positive and negative terminals (resistance load of $0.1\Omega$ ), monitoring the battery temperature changes in the course of test. End the test when the battery temperature drops to about $10^{\circ}\text{C}$ lower than peak value.
5.3.3	Heating	No fire or explosion	Cell is heated in a circulating air oven at a rate of $(5\pm2)^{\circ}$ C per minute to $130\pm2^{\circ}$ C, and then placed for 30 minutes at $130\pm2^{\circ}$ C
5.3.4	-	No leakage, no fire or explosion	After full charge, place the battery in the temperature control box of $20\pm5^{\circ}\text{C}$ , do the following steps:  (1)Put the battery into test chamber of $75^{\circ}\text{C}\pm2^{\circ}\text{C}$ and keep for 6h.  (2)Lower the temperature to $-40\pm2^{\circ}\text{C}$ and keep for 6h.  (3)Temperature conversion time is no longer than 30 min.  (4)Repeat the above three steps for 10 cycles.

Note: Unless otherwise specified, all tests stated in this specification are conducted at the following conditions: Temp. :  $20\pm5$  °C; Relative Humidity:  $25\%\sim85\%$ .

#### **6. Battery shipment voltage:** 3.83~3.9V

#### 7. Shelf life

One year warranty after the date of production

#### 8. Matters needing attention

Strictly observes the following notes. EEMB are not responsible for any accident due to the handling disagreed with this instruction.

# ! Danger

- Strictly prohibits heat or throw cell into fire.
- Strictly prohibits throw and wet cell in liquid such as water, gasoline or drink etc.
- Strictly prohibits use or leave cell close to fire or inside of a car with temperature above 60°C. Also do not charge / discharge in such conditions.
- Strictly prohibits put batteries in your pockets or bags together with metal objects such as necklaces, hairpins, coins, or screws. Do not store or transport batteries with the above objects.
- Strictly prohibits short circuit the (+) and (-) terminals with metals.
- Do not place Cell in a device with the (+) and (-) in reverse.



<b>Document Name</b>	Document No.	Ver	Date	Page
LP402040 Specification	ZJQM-RD-SPC-A0747	0.0	2015-2-11	6/7

- Strictly prohibits pierce Cell with sharp objects such as a needle.
- Strictly prohibits disassemble the cell.
- Strictly prohibits welding a cell directly.
- Do not use a Cell with serious scar or deformation.
- Please read the user's manual thoroughly before usage, inaccurate handling of lithium ion rechargeable cell may cause leakage, heat, smoke, an explosion, or fire, capacity decreasing.

#### ! Warning

- Strictly prohibits put cell into a microware oven, dryer, or high-pressure container.
- Strictly prohibits use cell with dry cells and other primary batteries, or new and old battery or batteries of a different package, type, or brand.
- Stop charging the Cell if charging is not completed within the specified time.
- Stop using the Cell if abnormal heat, odor, discoloration, deformation or abnormal condition is detected during use, charge, or storage.
- Keep away from fire immediately when leakage or foul odor is detected.
- If liquid leaks onto your skin or clothes, wash well with fresh water immediately.
- If liquid leaking from the Cell gets into your eyes, do not rub your eyes. Wash them well with clean edible oil and go to see a doctor immediately.

#### ! Caution

- Before using the Cell, be sure to read the user's manual and cautions on handling thoroughly.
- Charging with specific charger according to product specification. Charge with CC/CV method.
   Strictly prohibits revered charging. Connect cell reverse will not charge the cel. At the same time, it will reduce the charge-discharge characteristics and safety characteristics, this will lead to product heat and leakage.
- Store batteries out of reach of children so that they are not accidentally swallowed.
- If younger children use the Cell, their guardians should explain the proper handling.
- Before using the Cell, be sure to read the user's manual and cautions on handling thoroughly.
- Batteries have life cycles. If the time that the Cell powers equipment becomes much shorter than usual, the Cell life is at an end. Replace the Cell with a new same one.
- When not using Cell for an extended period, remove it from the equipment and store in a place with low humidity and low temperature.
- While the Cell pack is charged, used and stored, keep it away from objects or materials with static electric charges.
- If the terminals of the Cell become dirty, wipe with a dry clothe before using the Cell.
- Storage the cells in storage temperature range as the specifications, After full discharged, we suggest that charging to 3.7~4.0V with no using for a long time.
- Battery should be charged and discharged every 3 months at 0.2 C during long term storage, and then charge to 50-70% of the capacity for storage.
- Do not exceed these ranges of the following temperature ranges:

Charge temperature range :  $0^{\circ}$ C to  $45^{\circ}$ C;

Discharge temperature range :  $-20^{\circ}$ C to  $60^{\circ}$ C.

Store less than 1 month :  $-20^{\circ}\text{C} - +60^{\circ}\text{C}$ 



Document Name	Document No.	Ver	Date	Page
LP402040 Specification	ZJQM-RD-SPC-A0747	0.0	2015-2-11	7/7

Store less than 3 months :  $-20^{\circ}\text{C}$  -  $+45^{\circ}\text{C}$ Store less than 1 year :  $-20^{\circ}\text{C}$  -  $+25^{\circ}\text{C}$ 

# ! Special Notice

Keep the cells in 50% charged state during long period storage. We recommend to charge the battery up to 50% of the total capacity every 3 months after receipt of the battery and maintain the voltage 3.7~4.0V. And store the battery in cool and dry place.