

Document Name	Document No.	Ver	Date	Page
LP8545135 Specification	ZJQM-RD-SPC-2569	0.0	2014/8/4	1/6

EEMB CO., LTD

Polymer Li-ion Battery Specification

Model: LP8545135

Capacity: 5300mAh

Prepared	Checked	Approved
Mike Cai	Tina Cheng	Alex Lee

Customer:

Customer Approval (Customer confirmation) :				
Signature	Checked	Approved		

Address:Room ABCD,25/F, Block A, Fortune Plaza, NO.7060 Shennan Road Shenzhen, ChinaPostal code:518040Phone:0086-755-83022275FAX:0086-755-83021966


http://www.eemb.com



Document Name	Document No.	Ver	Date	Page
LP8545135 Specification	ZJQM-RD-SPC-2569	0.0	2014/8/4	2/6

Catalog

Chapter	Content	Page
0	Catalog	2
1	Scope	3
2	Product Basic Characteristics	3
2.1	Model	3
2.2	Capacity	3
2.3	Nominal Voltage	3
2.4	Weight	3
2.5	Internal Impedance	3
2.6	Dimension	3
2.7	Charge	3
2.8	Discharge	3
2.9	Operation Temperature	3
2.10	Storage Temperature	3
2.11	Storage Relative Humidity	3
3	Shape and Dimensions	3
4	Appearance	3
5	Specification	4
5.1	Electrical Characteristics	4
5.1.1	1C ₅ A rate discharge capacity	4
5.1.2	High temp. discharge capacity	4
5.1.3	Low temp. discharge capacity	4
5.1.4	Cycle Life	4
5.1.5	Capacity Retention	4
5.2	Acclimatization Characteristics	4
5.2.1	High Temp. and High Humidity	4
5.2.2	Vibration	4
5.2.3	Drop	4
5.3	Safety Characteristics	5
5.3.1	Overcharge	5
5.3.2	Short-Circuit	5
5.3.3	Heating	5
6	Matters needing attention	5-6



1. Scope


This product specification defines the requirements of the rechargeable polymer lithium-ion battery supplied to the customer by EEMB Co., Ltd..

2. Product Basic Characteristics

No.		Item	Characteris	tics	Remark
2.1		Model	LP8545135		
2.2	Conositu	Nominal Capacity	5300	mAh	0.2C ₅ A
2.2	Capacity	Minimum	5100	mAh	0.2C ₅ A
2.3	Non	ninal Voltage	3.7	V	
2.4		Weight	Approx. 106	g	
2.5	Interr	al Impedance	\leq 60	mΩ	AC 1KHz (50%charge)
		Length	≤ 136	mm	
2.6	Dimension	Width	≤ 45.5	mm	
		Thickness	\leq 8.0	mm	
	Charge	Maximum Current	5300	mA	$1C_5A$ (CC&CV)
2.7		Limited Voltage	4.200±0.020	V	
		End-of Current	106	mA	
2.8	Discharge	Maximum Current	10600	mA	2.0C ₅ A
2.0	Discharge	End Voltage	2.75±0.005	V	
2.9	Operation	Charge	$0 \sim 45$	°C	
2.9	Temperature	Discharge	$-20 \sim +60$	°C	
	Storage	1 month	-20~+60	°C	
2.10	Storage Temperature	3 month	-20 ~ +45	°C	
	remperature	12 month	-20 ~ +25	°C	
2.11	Storage F	Relative Humidity	65±20	%	

3. Shape and Dimensions (Unit: mm)

Item	Specification
Т	Max8.0
W	Max45.5
L	Max136
L1	Max137
L2	10±1
М	27±1
N	5±0.5





Document Name	Document No.	Ver	Date	Page
LP8545135 Specification	ZJQM-RD-SPC-2569	0.0	2014/8/4	4/6

4. Appearance

It shall be free from any defects such as remarkable scratches, breaks, cracks, discoloration, leakage, or middle deformation.

5. Specificatio

5.1 Electrical Characteristics

No.	Item	Criteria	Test Instructions
5.1.1	1C ₅ A rate discharge capacity	Discharge Time≥57min	Full charge at $20\pm5^{\circ}$ C, rest for 60 min, then discharge at the same temperature with $1.0C_5$ A to 2.75V.
5.1.2	High temp. discharge capacity	Discharge Time≥54min	Full charge at 20 ± 5 °C, store at 55 ± 2 °C for 2h, then discharge at the same temperature with $1.0C_5A$ to 2.75V.
5.1.3	Low temp. discharge capacity	Discharge Time≥4.25h	Full charge at 20 ± 5 °C, store at -10 °C ±2 °C for 16h~24h, then discharge at the same temperature with $0.2C_5A$ to 2.75V
5.1.4	Cycle Life	≥500 Cycles (0.5C₅A) ≥800 Cycles (0.2C₅A)	After full charge, rest for 10 min, then discharge at constant current to 2.75V, rest for 10 minutes. Repeat above steps until the two consecutive cycles of discharge time is less than the regulated time. (500 cycles≥96min,800 cycles≥240min)
5.1.5	Capacity Retention	Discharge Time≥4.5 h	After full charge, store at 20 ± 5 °C for 28 days. Then discharge with $0.2C_5A$ to $2.75V$

5.2 Acclimatization Characteristics

No.	Item	Criteria	Test Instructions
5.2.1	High Temp, and High	no fire or explosion;	After full charge, store at $40^{\circ}C \pm 2^{\circ}C(90\% \sim 95\% RH)$ for 48h. After test, place at $20^{\circ}C \pm 5^{\circ}C$ for 2h and then discharge with $1C_5A$ to end-voltage
5.2.2		No damnification, leakage, no fire or explosion; Battery Voltage>3 6V	Batteries are vibrated 30 min in three mutually perpendicular directions with amplitude of 0.38mm (10~30Hz) or 0.19mm (30~55Hz) and the scanning rate of 1 oct per min
5.2.3		explosion.	Batteries are dropped onto a hard board with the thickness of 18~20mm from 1 meter



IM	Document Name	Document No.	Ver	Date	Page
	LP8545135 Specification	ZJQM-RD-SPC-2569	0.0	2014/8/4	5/6

5.3 Safety Characteristics

No.	Item	Criteria	Test Instructions
5.3.1	Overcharge	No fire or explosion	Charged the cells at $3C_5A$ current 20 ± 5 °C with a voltage limit of 4.8V and Current close to 0 A
5.3.2	Short-Circuit	The maximum Temperature:	Batteries are short-circuited by connecting the positive and negative terminals for 1h with a resistance load of 0.1Ω
5.3.3	Heating	No fire or explosion	Cell is heated in a circulating air oven at a rate of $(5\pm2)^{\circ}$ per minute to 130°C, and then placed for 30 minutes at 130°C

Note: Unless otherwise specified, all tests stated in this specification are conducted at the following conditions: Temp. : 20 ± 5 °C; Relative Humidity: $25\% \sim 85\%$.

6. Matters needing attention

Strictly observes the following needing attention. EEMB will not be responsible for any accident occurred by handling outside of the precautions in this specification.

! Danger

- Strictly prohibits heat or throw cell into fire.
- Strictly prohibits throw and wet cell in liquid such as water, gasoline or drink etc.
- Strictly prohibits use leave cell close to fire or inside of a car where temperature may be above 60°C. Also do not charge / discharge in such conditions.
- Strictly prohibits put batteries in your pockets or a bag together with metal objects such as necklaces. Hairpins, coins, or screws. Do not store or transportation batteries with such objects.
- Strictly prohibits short circuit the (+) and (-) terminals with other metals.
- Do not place Cell in a device with the (+) and (-) in the wrong way around.
- Strictly prohibits pierce Cell with a sharp object such as a needle.
- Strictly prohibits disassemble or modify the cell.
- Strictly prohibits welding a cell directly.
- Do not use a Cell with serious scar or deformation.
- Thoroughly read the user's manual before use, inaccurate handling of lithium ion rechargeable cell may cause leakage, heat, smoke, an explosion, or fire, capacity decreasing.

! Warning

- Strictly prohibits put cell into a microware oven, dryer, or high-pressure container.
- Strictly prohibits use cell with dry cells and other primary batteries, or new and old battery or batteries of a different package, type, or brand.
- Stop charging the Cell if charging is not completed within the specified time.
- Stop using the Cell if abnormal heat, odor, discoloration, deformation or abnormal condition is detected during use, charge, or storage.
- Keep away from fire immediately when leakage or foul odor is detected.

∃Етз	Document Name	Document No.	Ver	Date	Page
	LP8545135 Specification	ZJQM-RD-SPC-2569	0.0	2014/8/4	6/6

- If liquid leaks onto your skin or clothes, wash well with fresh water immediately.
- If liquid leaking from the Cell gets into your eyes, do not rub your eyes. Wash them well with clean edible oil and go to see a doctor immediately.

! Caution

- Before using the Cell, be sure to read the user's manual and cautions on handling thoroughly.
- Charging with specific charger according to product specification. Charge with CC/CV method. Strictly prohibits revered charging. Connect cell reverse will not charge the cel. At the same time, it will reduce the charge-discharge characteristics and safety characteristics, this will lead to product heat and leakage.
- Store batteries out of reach of children so that they are not accidentally swallowed.
- If younger children use the Cell, their guardians should explain the proper handling.
- Before using the Cell, be sure to read the user's manual and cautions on handling thoroughly.
- Batteries have life cycles. If the time that the Cell powers equipment becomes much shorter than usual, the Cell life is at an end. Replace the Cell with a new same one.
- When not using Cell for an extended period, remove it from the equipment and store in a place with low humidity and low temperature.
- While the Cell pack is charged, used and stored, keep it away from objects or materials with static electric charges.
- If the terminals of the Cell become dirty, wipe with a dry clothe before using the Cell.
- Storage the cells in storage temperature range as the specifications, After full discharged, we suggest that charging to 3.7~4.0V with no using for a long time.
- Do not exceed these ranges of the following temperature ranges:

Charge temperature range : 0° C to 45° C; Discharge temperature range : -20° C to 60° C. Store less than 1 month : -20° C - $+60^{\circ}$ C Store less than 3 months : -20° C - $+45^{\circ}$ C Store less than 1 year : -20° C - $+25^{\circ}$ C

! Special Notice

Keep the cells in 50% charged state during long period storage. We recommend to charge the battery up to 50% of the total capacity every 3 months after receipt of the battery and maintain the voltage 3.7~4.0V. And store the battery in cool and dry place.